



Instructions for Application of Binary UniCoat PSP in an Aerosol Can (Product ID: BUNC-12)

Warning: Use with adequate ventilation or appropriate respiratory protection. This product is flammable; do not spray near flame, heat, or sparks. This product contains solvents and propellants that may damage some plastic surfaces.

Directions:

1. Clean the model, calibration coupons, and a small test piece. We suggest acetone or alcohol on wipes.
2. Hold the can firmly and shake vigorously for 60 seconds. Swirl the bottom of the can to ensure that the ball is traveling freely.
3. Test your spray method on a test piece of metal. Keep the can about 18 inches (46 cm) away from surface while spraying.
4. Over the bare metal surface of the test piece, apply about 5 to 7 (very light) cross coats. Cross coats means working from left to right/right to left while moving down the model, then work back up left to right/ right to left. This constitutes one coat. The next coat is applied top to bottom/ bottom to top in a similar manner. For best results, apply light coats, allow paint to dry between coats (~10 sec.), and STOP when you have good coverage.
5. Before storing spray can, spray with the can inverted for 10 seconds or until only clear propellant emerges from the can. This will keep the nozzle clear.

Most common reasons for Binary UniCoat paint failure:

1. Rash or Spots.

Can was not shaken as described. The failure will look like a skin rash. You will see small areas where the aerosol-can-propellant will "displace" the paint. This is difficult to cover with more layers.

2. Runs or Sags.

This is generally caused by applying a heavy or wet coat. Use lighter coats, move the can away from the surface, or move the can over the surface faster.

3. Grease or oil on surface.

May not notice this by eye, but the temperature and pressure sensitivity of the paint will be compromised. Clean and repaint.

Innovative Scientific Solutions, Inc.

7610 McEwen Road
Dayton, OH 45459
Phone:(937) 630-3012
Email: painting@innssi.com